In the Claims:

1. (currently amended) A method of forming a dried, resilient, glossy coating <u>having</u> a tensile strength of greater than or equal to 500 psi on a tire, comprising,

applying an aqueous_based tire dressing composition to a surface of a tire, the aqueous_based tire-dressing composition comprising a film-forming polymer liquid dispersion selected from the group consisting of aqueous polyurethane dispersions or aqueous urethane acrylic copolymers and an antifoaming agent.

- 2. (canceled)
- 3. (canceled)
- 4. (original) The method of claim 3 wherein the antifoaming agent is selected from the group consisting of silcone defoamers, silicone antifoamers, non-silicone defoamers, non-silicone antifoamers and mixtures thereof.
- 5. (withdrawn) The method of claim 1 wherein said composition further comprises a wetting agent.
- 6. (withdrawn) The method of claim 5 wherein the wetting agent is selected from the group consisting of non-ionic wetting agents, non-silicone wetting agents and mixtures thereof.
- 7. (withdrawn) The method of claim 1 wherein said composition further comprises a thickener.
- 8. (withdrawn) The method of claim 7 wherein the thickener is selected from the group consisting of acrylic acid-based polymers, hydroxyethylcellulose, polyacrylic-based thickeners, sodium silicate and mixtures thereof.
- 9. (withdrawn) The method of claim 1 wherein said composition further comprises a pigment.
- 10. (withdrawn) The method of claim 9 wherein the pigment is selected from the group consisting of titanium dioxide, carbon black, mica, zinc oxide, calcium carbonate, clay and mixtures thereof.
- 11. (withdrawn) The method of claim 1 wherein said composition further comprises a biocide.
- 12. (withdrawn) The method of claim 11 wherein the biocide is selected from the group consisting of 2-n-octyl-4-isothiazolin-3-one, Polyphase, cationic polymeric biocides, 1,2-benzisothiazolin-3-one, sodium 2-pyridinethiol-1-oxide and mixtures thereof.
- 13. (withdrawn) The method of claim 1 wherein said composition further comprises an antioxidant.

- 14. (withdrawn) The method of claim 13 wherein the antioxidant is selected from the group consisting of hindered phenols, hindered aromatic amines and mixtures thereof.
- 15. (withdrawn) The method of claim 1 wherein said composition further comprises a ultraviolet/visible light stabilizer.
- 16. (withdrawn) The method of claim 15 wherein the light stabilizer is selected from the group consisting of carbon black, micronized titanium dioxide, organic stabilizer compounds and mixtures thereof.
- 17. (withdrawn) The method of claim 1 wherein said composition further comprises a coalescent.
- 18. (withdrawn) The method of claim 17 wherein the coalescent is selected from the group consisting of ester alcohols, glycol methyl ethers and mixtures thereof.
- 19. (withdrawn) The method of claim 1 wherein said composition further comprises a plasticizer.
- 20. (withdrawn) The method of claim 19 wherein the plasticizer is selected from the group consisting of polypropylene glycol dibenzoate, alkyl benzyl phthalates, 2,2,4-trimethyl-1,3-pentanediol diisobutyrate, bis(2-ethylhexyl) phthalate, benzoate esters, and mixtures thereof.
- 21. (withdrawn) The method of claim 1 wherein said composition further comprises an adhesion promoter.
- 22. (withdrawn) The method of claim 21 wherein the adhesion promoter is selected from the group consisting of aminopropyltriethoxysilane, diaminosilane, triaminosilane, chlorosilane, organofunctional silane, alkylsilanes and mixtures thereof.
- 23. (withdrawn) The method of claim 1 wherein said composition further comprises a leveling agent.
- 24. (withdrawn) The method of claim 23 wherein the leveling agent is selected from the group consisting of polyamides, tributoxyethyl phosphate and mixtures thereof.
- 25. (currently amended) The method of claim 1 wherein the tire surface is not pretreated to functionalize or polarize the elastomers on the tire surface comprising elastomers.